



PTU-UB™

CHEMICAL RESISTANT SPRAY APPLIED POLYTHIOUREA ELASTOMER

Patents Pending
Revised 3/03/14

DESCRIPTION

PTU-UB™ pure polyurea is a new generation of high-performance polyurea coating and is the result of six years of development and field testing. This chemical resistant coating provides high-ductility, allowing it to move with expanding and contracting surfaces. PTU-UB™ is formulated to provide a tenacious bond to certain thermoset plastic surfaces. PTU-UB™ can be sprayed to any thickness in one application and returned to service in a matter of hours.

FEATURES

- A elastomer with chemical resistance. Comparable to many epoxies.
- Self-priming in most instances, with strong adhesion.
- Return to service within hours not days (foot traffic 1 hour; vehicle traffic 4 hours).
- Typically applied in a single 'multi-pass' application.
- Eco-friendly, 100% solids. No VOCs.

RECOMMENDED USES

- Primary and secondary containment
- Steel tanks, concrete tanks, and silos
- Barge and ship holds
- Oil and gas pipelines
- Waste water treatment facilities
- Chemical transportation
- Industrial flooring
- Pulp and paper industry
- Asbestos and lead encapsulation

Examples of PTU-UB™ immersion in some common reagents

CHEMICAL	WEIGHT GAIN %	
	Weight Gain	Duration
Acetic 50%	9.75%	11 months
Diesel	0.1%	3 years
Gasoline (unleaded)	4.75%	17 months
Sulphuric Acid 14% Phosphoric Acid 30%	- 0.86%	2 years
Jet Fuel JP-1,2,3	1.4%	5 years
JP-7 Jet Fuel (w/60% Toluene)	8.67%	19 months
Methanol	9.12%	19 months
Skydrol	16.5%	1 year
Sulphuric Acid 50%	6.15%	1 year

Immersion samples were 'free films' (6 sides exposed). In service, containment liners have only one side of liner exposed to reagents. To calculate approximate chemical absorption, divide the weight gain percentage indicated on the adjacent chart by two. All tests performed at SPI location at room temperature. Certified free film samples are available for immersion evaluation.

WET PROPERTIES @ 77°F (25°C)

Solids by Volume	100%
Solids by Weight	100%
Volatile Organic Compounds	0 lbs/gal (0g/l)
Theoretical Coverage DFT	100 sq. ft. @ 16 mils/gal
Weight per gallon (approx.)	9.6 lbs. (4.35 kg)
Number of Coats	1 or more
Mix Ratio	1 "A": 1 "B"
Viscosity (cps) @ 77° F (25 °C)	A: 900 ± 50 cP B: 950 ± 50 cP
Shelf Life Unopened Containers @ 60-90°F (15°-32°C)	Three months

Minimum material/container temperature for PTU-UB™ application is 70°F (21°C).

DRY PROPERTIES @ 70 mils (1.77 mm)*

Tensile Strength ASTM D638	>2500 psi (17.38 mpa)	
Elongation ASTM D638	88% approx.	
Permeance ASTM D96-80	Perms-inch 0.007	
Hardness (Shore A) ASTM D2240-81	98	
Hardness (Shore D) ASTM D2240-81	52	
Mandrel Bend ASTM D522-93a	Passed	Mandrel Size – 1" Test Temp -60°F (-51°C)

CURING SCHEDULE @ 70°F (21°C)

Gel	4 sec.
Tack Free	10 sec.
Post Cure**	12 - 24 hours
Recoat	0 min. - 6 hours

*All cured film properties are approximate since processing parameters, admixture types, and quantities will change physical properties of the cured elastomer. All samples for above tests were force cured or aged for more than one week, it is recommended that the user perform their own independent testing. The samples for tests were sprayed with Graco HXP3P @ 2700 psi dynamic. Primaries/Hose Heat 170°F (77°C), MP Fusion gun with 29/29 40 mixing chamber and .040 ceramtip. Test results from SPI.

Note: Currently, this product is manufactured exclusively in our Lakewood, Washington facility. Therefore, please allow additional transit time and additional transportation charges to certain geographic areas.

**Complete polymerization to achieve final strength can take up to several days or weeks, depending on a variety of conditions or product type.

COLOR

PTU-UB™ is available in SPI standard colors. Custom colors will be quoted upon request. It should be noted that PTU-UB™ is an aromatic polyurea; therefore, as with all aromatics, color change and superficial oxidation will occur.

SPECIALTY PRODUCTS, INC., 2410 104TH Street Ct. S. Ste. D, Lakewood, WA. 98499 1-800-627-0773

www.specialty-products.com info@specialty-products.com

SPI Manufacturing/Distribution Locations: Lakewood, WA · Rowlett, TX · Anchorage, AK

© 2013 Specialty Products, Inc.

GENERAL APPLICATION INSTRUCTIONS

PTU-UB™ applicators must be trained and certified by SPI. Apply PTU-UB™ only to clean, dry, sound surfaces free of loose particles or other foreign matter. A primer may be required depending on type and/or condition of the substrate. Consult technical service personnel for specific primer recommendations and substrate preparation procedures.

Apply PTU-UB™ when surface and air temperature is above 40°F (4°C) and rising and 7°F (-13°C) above dew point.

It is recommended that PTU-UB™ be sprayed in multi-directional (north-south/east-west) passes to ensure uniform thickness.

The polyol "B" component must be thoroughly power mixed each day, prior to use. Contact a SPI technician regarding proper mixing equipment.

Follow the instructions attached to "A" and "B" containers.

RECOMMENDED EQUIPMENT AND SETTINGS

- Standard 1:1 ratio, heated, plural-component equipment developing a minimum of 2500 psi dynamic pressure (13.90 mpa) with heating capabilities to 165° F (74 °C) will adequately spray PTU-UB™. These include Graco HXP3, HXP2, and EXP2. Gun models include Graco Fusion MP, GX7-DI and Gusmer GX7-400.
- Pre-heater temperature should be at 160-170°F (71-76 °C).
- Hose temperature should be at 160 -170° F (71-76°C). A hose thermometer inserted under the insulation near the gun should read a minimum of 145-155°F (63-68°C).
- Physical properties will be enhanced when sprayed at higher pressure (3000 psi or more) (20.8mpa), utilizing an impingement mix gun such as the MP Fusion or GX7-DI.

MIXING AND THINNING

The polyol "B" component must be thoroughly power mixed each day, prior to use. Contact a SPI technician regarding proper mixing equipment.

Thinning is not required. Using any thinner may adversely affect product performance.

GENERAL SAFETY, TOXICITY & HEALTH DATA

Safety Data Sheets are available for this coating material. Any individual who may come in contact with these products should read and understand the M.S.D.S. **CHEMTREC EMERGENCY NUMBER 1-800-424-9300**

WARNING: Contact with skin or inhalation of vapors may cause an allergic reaction. Avoid eye contact with the liquid or spray mist. Hypersensitive persons should wear protective clothes, gloves and use protective cream on face, hands and exposed areas.

CLEAN UP: Use DPM, NMP, and Polyclean.

EYE PROTECTION: Safety glasses, goggles, or a face shield are recommended.

SKIN PROTECTION: Chemical resistant gloves are recommended. Cover as much of the exposed skin area as possible with appropriate clothing.

RESPIRATORY PROTECTION: Use a respirator approved for isocyanates and organic vapors. If you are not sure or not able to monitor levels, or if you are spraying in an enclosed/indoor area, use MSHA/NIOSH approved supplied

air respirator. Consider the application and environmental concentrations in deciding if additional protective measures are necessary.

INGESTION: Do not take internally. It is believed that ingestion of polymeric isocyanates would not be fatal to humans, but may cause inflammation of mouth and stomach tissue.

LIMITATIONS

- PTU-UB™ applicators must be trained and certified by SPI.
- This product is for professional use only.
- This product must be stored at temperatures between 60° F to 90° F (15 °C to 32 °C).
- Minimum material/container temperature for spray application is 70°F (21 °C).
- Avoid moisture contamination in containers. Containers should not be resealed if contamination is suspected, CO₂ created pressure can develop. Do not attempt to use contaminated material.
- Liquid components exposed to undried air will result in reduced physical properties of the cured coating.
- Apply PTU-UB™ when surface and air temperatures are above 40°F (5°C) and rising, and 7°F (-13°C) above dew point.

Note: The material supplied is two components (Component "A"/Component "B") used to formulate this product. The quality and characteristics of the finished polymer is determined by the mixture and application of the two components.

WARRANTY & DISCLAIMER

Specialty Products, Inc. has no role in the manufacture of the finished polymer other than to supply its two components. It is vital that the person applying this product understands the product, and is fully trained and certified in the use of plural-component equipment.

Specialty Products, Inc., an Alaska corporation, warrants only that the two components of this product shall conform to the technical specifications published in the product literature.

The quality and fitness of the product are dependent upon the proper mixture and application of the components by the applicator. There are no warranties that extend beyond the description on the face of this instrument.

Failure to apply the product within the parameters stated on this document shall void the warranty.

SPECIALTY PRODUCTS, INC. MAKES NO WARRANTY OF MERCHANTABILITY OF THE PRODUCT OR OF FITNESS OF THE PRODUCT FOR ANY PARTICULAR PURPOSE.

Specialty Products, Inc. makes no warranty as to the quality of any product modified, supplemented, tinted, or altered in any way after it leaves the manufacturing plant.

Specialty Products, Inc. does not warrant that this product is suitable for use as a liner for potable water containers. Use of this product in a potable water container could be hazardous to health if it is improperly processed or applied.

The liability of Specialty Products, Inc. for any nonconformity of the product to its technical specifications shall be limited to replacement of the product.

The sole exclusive remedy of buyer, which is to have Specialty Products, Inc. replace any nonconforming product at no cost to buyer, is conditioned upon buyer notifying Specialty Products, Inc. or its distributor in writing of such defect within thirty days of the discovery of such defect.

Specialty Products, Inc. shall not be liable for any direct, incidental, or consequential damages resulting from any breach of warranty.

The data presented herein is intended for professional applicators or those persons who purchase or utilize this product in the normal course of their business.

The potential user must perform any pertinent tests in order to determine the product's performance and suitability in the intended application, since final determination of fitness of the product for any particular use is the responsibility of the buyer.

The aforementioned data on this product is to be used as a guide and is subject to change without notice.

The information herein is believed to be reliable, but unknown risks may be present. Specialty Products, Inc. makes no warranties, expressed or implied, including patent warranties or warranties of merchantability or fitness of use, with respect to products or information set forth herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.

Accordingly, the buyer assumes all risks whatsoever as to the use of these materials and buyer's exclusive remedy as to any breach of warranty, negligence, or other claim shall be limited to the purchase price of the materials. Failure to adhere to any recommended procedures shall relieve Specialty Products, Inc. of all liability with respect to the materials and the use thereof.

**SPI - The Single Source Solution Since
1974 Serving the Plural-Component Industry**



**Product & Equipment Technical Assistance
24 hours – 7 days a week (800) 627-0773**



SPI WEBSITE



A&B MSDS