



STAINGARD 6000™

ALIPHATIC POLYASPARTIC POLYUREA TOPCOAT

Revised 06.29.11

DESCRIPTION

STAINGARD 6000™ is a 100% solids by volume, aliphatic polyaspartic coating, two component, liquid applied, environmentally friendly surface topcoat for waterproofing membrane systems, with a citrus odor. STAINGARD 6000™ is quick curing and specifically formulated to be installed in thin film applications.

FEATURES

- Quick cure
- High tensile strength
- Color stable
- High gloss
- Abrasion resistant
- Topcoat over aromatic polyurea, polyurethane and epoxy applications ranging from 35° - 130°F, service temperature 0° - 200°F
- Very durable
- Excellent weather-ability
- Seamless waterproofing membrane
- UV resistance for superior gloss retention
- Meets California AQMD requirements

RECOMMENDED USES

- Concrete
- Plywood
- Steel
- Plastic
- Cold Storage Areas
- Food Processing Areas
- Industrial Warehouses
- Pulp and Paper Mills
- Chemical Plants
- Fertilizer Plants
- Off-Shore Oil Platforms
- Pipeline Barges

COLORS

STAINGARD 6000™ is available in Clear, Dolphin Grey, and Tan. Custom colors available upon request. Minimum order of 200 gallons (380 liters).

Packaging: 2 gallon kit (7.56 liter): 1 gallon (3.78 liter) part A and 1 gallon (3.78 liter) part B.

10 gallon kit is not an in-stock item and is available on large orders.

STAINGARD 6000 (clear)

Coverage Rate	See Guide Specifications
Dry Film Thickness, exclusive of aggregate @ 1 gal/100 sq. ft.	16 mils 406 microns
Pot Life at 75°F (24°C), 50% RH	10 - 15 minutes
Hardness, ASTM D-2240	65 +/- 2 Shore D
Tear Resistance, Die C, ASTM D-624	400 +/- 50 pli 70 +/- 10 kN/m
Tensile Strength, ASTM D-412	3000 +/- 200 psi 20.7 +/- 2 MPa
Ultimate Elongation, ASTM D-412	70 +/- 10%
Specific Gravity, Side A	1.1
Side B	1.05
Total Solids by Weight, ASTM D-2369	100%
Total Solids by Volume, ASTM D-2697	100%
Viscosity at 75°F (24°C)	
Side A	2600 +/- 300 cps
Side B	1100 +/- 300 cps
VOC's ASTM D-2369-81	0 lb/gal 0 gm/liter

STAINGARD 6000 (pigmented)

Coverage Rate	See Guide Specifications
Dry Film Thickness, exclusive of aggregate @ 1 gal/100 sq. ft.	16 mils 406 microns
Pot Life at 75°F (24°C), 50% RH	10 - 15 minutes
Hardness, ASTM D-2240	65 +/- 2 Shore D
Tear Resistance, Die C, ASTM D-624	375 +/- 50 pli 65.6 +/- 10 kN/m
Tensile Strength, ASTM D-412	2600 +/- 200 psi 17.9 +/- 2 MPa
Ultimate Elongation, ASTM D-412	30 +/- 10%
Specific Gravity, Side A	1.1
Side B	1.24
Total Solids by Weight, ASTM D-2369	100%
Total Solids by Volume, ASTM D-2697	100%
Viscosity at 75°F (24°C)	
Side A	2600 +/- 300 cps
Side B	2000 +/- 300 cps
VOC's ASTM D-2369-81	0 lb/gal 0 gm/liter



SPI - The Single Source Solution Since 1974
Serving the Plural Component Industry

Product & Equipment Technical Assistance
24 hours / 7 days a week (800) 627-0773

GENERAL APPLICATION INSTRUCTIONS

STAINGARD 6000™ can be applied by phenolic resin core roller, high pressure spray, or through a cup gun under low pressure. STAINGARD 6000™ should be applied at a minimum film thickness of 5 mils. It should be noted that the heavier the application, the longer the curing process takes.

Apply STAINGARD 6000™ evenly over the entire deck. For best results, airless sprayer or phenolic resin core roller may be used but extra care should be taken not to cause air bubbles.

MIXING

STAINGARD 6000™ may not be diluted under any circumstance. **DO NOT ESTIMATE, proportions are premeasured.** STAINGARD 6000™ Part A and Part B should be mixed individually before combining. Add Part B to Part A while mixing, using a mechanical mixer (Jiffy Mixer) at medium speeds. Mix until a homogenous mixture and color is obtained (at least 5 minutes) and mix frequently during application to maintain uniform color. Use care to scrape the sides of the container to ensure that no unmixed material remains. Use caution not to whip too much air into the material as this may result in pinhole blisters or shortened potlife.

DO NOT mix any material that cannot be used within 5 minutes.

CURING

At 70°F (21°C) and 50% relative humidity, allow each coat to cure a minimum of 2 – 4 hours between each coat.

Allow a minimum of 6 hours before permitting light pedestrian traffic and at least 24 – 48 hours before permitting heavy pedestrian traffic on to the finished surface.

Uncured STAINGARD 6000™ is very sensitive to heat and moisture. Higher temperatures and/or high humidity will accelerate the cure time. Use caution in batch sizes and thickness of application.

Low temperature and/or low humidity extend cure time.

EQUIPMENT CLEANUP

Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

STORAGE

STAINGARD 6000™ has a shelf life of 6 months from date of manufacture in original, factory sealed containers.

LIMITATIONS

Mix no more material than can be used within 5 minutes. Surface must be dry, clean, and free of foreign matter.

Clear coating may turn opaque and cloudy due to moisture penetration, especially in exterior applications.

Surface may be slippery when wet.

Containers that have been opened must be used as soon as possible.

Do not dilute under any circumstance.

WARNING

This product contains isocyanates and solvent.

WARRANTY & DISCLAIMER

Specialty Products, Inc. has no role in the manufacture of the finished polymer other than to supply its two components. It is vital that the person applying this product understands the product and is fully trained and certified in the use of plural component equipment.

Specialty Products, Inc., an Alaska corporation, warrants only that the two components of this product shall conform to the technical specifications published in the product literature.

The quality and fitness of the product are dependent upon the proper mixture and application of the components by the applicator. There are no warranties that extend beyond the description on the face of this instrument.

SPECIALTY PRODUCTS, INC. MAKES NO WARRANTY OF MERCHANTABILITY OF THE PRODUCT OR OF FITNESS OF THE PRODUCT FOR ANY PARTICULAR PURPOSE.

Specialty Products, Inc. makes no warranty as to the quality of any product modified, supplemented, tinted, or altered in any way after it leaves the manufacturing plant. Specialty Products, Inc. does not warrant that this product is suitable for use as a liner for potable water containers. Use of this product in a potable water container could be hazardous to health if it is improperly processed or applied.

The liability of Specialty Products, Inc. for any nonconformity of the product to its technical specifications shall be limited to replacement of the product.

The sole exclusive remedy of buyer, which is to have Specialty Products, Inc. replace any nonconforming product at no cost to buyer, is conditioned upon buyer notifying Specialty Products, Inc. or its distributor in writing of such defect within thirty days of the discovery of such defect.

Specialty Products, Inc. shall not be liable for any direct, incidental, or consequential damages resulting from any breach of warranty.

The data presented herein is not intended for non-professional applicators or those persons who do not purchase or utilize this product in the normal course of their business.

The potential user must perform any pertinent tests in order to determine the product's performance and suitability in the intended application, since final determination of fitness of the product for any particular use is the responsibility of the buyer.

The aforementioned data on this product is to be used as a guide and is subject to change without notice.

The information herein is believed to be reliable, but unknown risks may be present. Specialty Products, Inc. makes no warranties, expressed or implied, including patent warranties or warranties of merchantability or fitness of use, with respect to products or information set forth herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.

Accordingly, the buyer assumes all risks whatsoever as to the use of these materials and buyer's exclusive remedy as to any breach of warranty, negligence, or other claim shall be limited to the purchase price of the materials. Failure to adhere to any recommended procedures shall relieve Specialty Products, Inc. of all liability with respect to the materials and the use thereof.